



AquaCell® GL

Water-based Screen Printing Ink

Area of Application

Fast drying, water-based screen printing ink to print on paper, cardboard and wood. To be used for indoor and short term outdoor exposition.

Characteristics

- Good screen opening, even when printing fine details
- Good self solvency
- Good blocking resistance
- Energy saving due to low dryer temperature
- High printed speed
- VOCs reduced to approx. 2 – 3 %

Finish

Satin gloss

Color Shades

Basic Colors for the AquaCell® GL Matching System	093	Colorless	364	Red Dark	566	Blue Transparent
	160	Yellow Light	467	Pink Transparent	669	Green Transparent
	161	Yellow Dark	472	Violet	945	White
	362	Red Light	473	Pink Transparent	948	Black
Standard Colors	944	White Opaque				
Special Colors	777	Silver	878/013	Brillant Gold* ¹		
Process Inks	156	Process Yellow	558	Process Cyan	099	Process Paste
	357	Process Magenta	949	Process Black		
	777	Silver	878	Gold	878/042	Solar Gold
Pigment Concentrates	L 37486	Yellow	L 37488	Cyan	L 37489	Black
	L 37487	Magenta				

Thinning

1 % Defoamer L 54131 and 10 % water

or

1 % Defoamer L 54131 and 15 – 20 % Retarder L 47716

The defoamer is effective for approx. 3 days, then new defoamer should be added.

In addition, please refer to our technical leaflet "Printing with Water-based Screen Printing Inks" which may be downloaded from our website www.proell.de, click Downloads ⇒ Water-Based Screen Printing Inks ⇒ Printing with Water-Based Screen Printing Inks.

*¹ = Not in Stock, manufactured on request.

Fabric

PES-fabrics of 100 – 180 threads/cm (250 – 450 threads/inch) are suitable. When printing posters with process inks (paper weight of 130 – 150 g/m²) excellent results are achieved using polyester fabrics of 150 threads/cm (375 threads/inch).

The finer the mesh, the minor the ink deposit and the fluting of the paper.

Stencil

Water resistant emulsions must be used. Excellent results during long production runs are achieved by using Pröll Diazo-UV-Polymer Emulsion Norikop 7 S. Sufficient drying of the emulsion is essential, residual moisture before exposure reduces print run resistance. The exposure time should be as long as possible.

Directions for Processing and Drying

The humidity in the printing room should be at least 50 %, ideal conditions would be 60 – 70 %.

During long printing runs, an increase in viscosity caused by evaporation of water can be adjusted by the addition of water. Moreover during short printing stops, it is recommended to spray the screen surface with

During printing stops do not flood the stencil with ink. Before restarting to print, either wash with Aqua-Jet® Liquid Cleaner L 47603 or flood the stencil with fresh ink, let it take effect for two minutes and restart to print after some misprints.

Depending on the printing motif, papers up from circa 130 g/m² can be used. In general, drying equipment with a good air exchange and relatively low temperatures gives better results than dryers working with small amounts of air at high temperatures.

Printing on both sides of the substrate and stacking is not recommended.

Cleaning of Screens and Utensils

Screens and utensils can be cleaned with Aqua-Jet Liquid Cleaner L 47603 or Cleaning Concentrate 6953 (see Technical Information "Cleaning Concentrate 6953").

The screens may be cleaned in automatic screen washing and cleaning devices by using suitable cleaning agents.

For manual cleaning, the following advice is important:

- The non-squeegee-area should be kept as small as possible, e. g. confine the ink to the squeegee-area by using dams.
- The unused ink on both sides of the squeegee should be returned into the printing area from time to time.
- The unused ink on the screen should be protected from drying and hardening by spraying with water.

When manually cleaning Aqua-Jet Liquid Cleaner L 47603 or Cleaning Concentrate 6953 can be used. The above mentioned cleaners should be sprayed onto the stencil and spread with a brush. After soaking for 2 to 3 minutes, rinse with a high-pressure water sprayer.

Avoid eye and skin contact with alkaline cleaners, use personal protective equipment (e. g. gloves and glasses).

Auxiliaries

Defoamer L 54131

Add 1 % to ink before printing, stir thoroughly.

Retarder L 47716

Works like a retarder paste that is the viscosity of the ink is not dramatically decreased.

Add approximately 15 – 20 %.

Aqua-Jet® Liquid Cleaner L 47603

Cleaner with low content of solvents but good cleaning power.

Cleaning Concentrate 6953

Solvent free universal cleaner, can be diluted with water (see Technical Information).

Shelf Life

The shelf life stated on the label assures the ink's quality and refers to unopened original cans stored in a dry place at temperatures between 5 °C (40 °F) and 25 °C (75 °F).

Important

Allow the ink as well as all the auxiliaries to be added to adjust to room temperature in the closed container before use.

Printing results, to a large extent, depend on the substrate as well as the printing and application conditions. We recommend checking your printing materials under your conditions of use prior to any production runs. Materials that are supposed to be identical may vary from manufacturer to manufacturer and even from batch to batch. Some substrates may have been treated with or can contain sliding agents, antistatics or other additives which will impair the adhesion of the inks.

In general please refer to our technical leaflet "General Information on Screen Printing Inks" which may be downloaded from our website www.proell.de, click Downloads ⇒ Water-Based Screen Printing Inks.

Disposal

Before pouring waste into the sewage, it should be pretreated according to state-of-the-art technology.

Safety precautions – General indications:

When working with chemicals, the usual safety precautions are to be observed. These are besides the rules of the Accident Prevention & Insurance Associations a good ventilation of the work place as well as good skin care and protection.

The information contained in the technical information/instruction sheets or other product information sheets is based on product testing conducted by Pröll. Because printing and environmental factors critically affect each individual ink application, the above mentioned information and instructions represent only general recommendations concerning product characteristics and directions for use and should not be construed as representing express warranties regarding the product. The information and instructions in no way release the purchaser from his obligation to verify and test the inks and their application for the specific request, regarding: product characteristics, weather resistance, mixing proportions, gloss, thinning, special mixtures, printability, drying speed, cleaning, effects on or of other materials to be contacted and safety precautions. All details contained in the instruction sheet "General Information on Screen Printing Inks" are to be considered. The further manufacture and use of products containing our inks by the purchaser takes place beyond our control, and the responsibility for further application and use of our product resides solely with the purchaser. Pröll disclaims any warranties, express or implied.

This information supersedes all previous technical information.