

Auxiliary Products for Water-based Screen Printing Inks

Defoamer L 54131

For all water-based inks: 1 % addition

Do not use this defoamer for Aqua-Jet® KF and Aqua-Jet® WT!

Defoamer L 36273

For Aqua-Jet® KF and Aqua-Jet® WT, 1 % addition.

Crosslinker WB 001

For improving chemical and mechanical resistance of water-based screen printing inks. Adding crosslinker to textile inks leads to good washing resistance. Pot life amounts to approx. 8 hours.

Addition often improves adhesion which, however, can be worse than without crosslinker (e.g. in case of Aqua-Jet® KF on polystyrene).

For handling please follow the instructions of the material safety data sheet.

Retarder VZ 100

Solvent-based retarder, addition up to 5 %, slows drying in the mesh.

Not suitable for AquaCell® GL.

Retarder L 47716

Water-based retarder, free of solvents, for all water-based inks, addition 10 – 20 %. The retarder has the same effect as retarder paste since it does not lower the ink's viscosity.

Aqua-Jet® Liquid Cleaner L 47603

Cleaner for all water-based inks only dried in slightly having a solvent content of less than 6 %.

Cleaner Concentrate 6953

Cleaner Concentrate, **free of solvents**, can be thinned with water (please see the corresponding Technical Information).

Cleaner 6614

Solvent-based cleaner for ink residues dried into the mesh.

The mesh should be dry before cleaning.